

## CERTIFICIRANA LEPILA ZA EUROPO 2008

	<b>PURBOND® HB 221</b>	<b>PURBOND® HB 230</b>	<b>PURBOND® HB 530</b>	<b>PURBOND® HB 360</b>	<b>PURBOND® HB 480</b>	<b>PURBOND® HB 440</b>	<b>PURBOND® HB 120</b>	<b>PURBOND® HB 110</b>	<b>PURBOND® HB 181</b>	
Osnova	Poliuretan	Poliuretan	Poliuretan	Poliuretan	Poliuretan	Poliuretan	Poliuretan	Poliuretan	Poliuretan	
Oznaka	Isocianat prepolimer	Isocianat prepolimer	Isocianat prepolimer	Isocianat prepolimer	Isocianat prepolimer	Isocianat prepolimer	Isocianat prepolimer	Isocianat prepolimer	Isocianat prepolimer	
Komponentno	1 komponentno	1 komponentno	1 komponentno	1 komponentno	1 komponentno	1 komponentno	1 komponentno	1 komponentno	1 komponentno	
Barva lepila	rjavo-bež	bež	belo-bež	bež	belo-bež	belo-bež	belo-bež	belo-bež	rjavo-bež	
Barva lepilnega spoja	transparent	transparent	transparent	transparent	transparent	transparent	transparent	transparent	transparent	
Odprti čas <sup>1</sup>	<b>5 min</b>	<b>10 min</b>	<b>12 min</b>	<b>20 min</b>	<b>22 min</b>	<b>30 min</b>	<b>42 min</b>	<b>1 ura</b>	<b>2 uri</b>	
Čas stiskanja <sup>1</sup>	<b>15 min</b>	<b>20 min</b>	<b>1 ura</b>	<b>40 min</b>	<b>70 min</b>	<b>2 uri</b>	<b>135 min</b>	<b>3 ure</b>	<b>6 ½ ur</b>	
Končna trdnost [ur] <sup>1</sup>	12 hours	12 hours	12 hours	12 hours	12 hours	12 hours	12 hours	24 hours	48 hours	
Suha snov	100 %	100 %	100 %	100 %	100 %	100 %	100 %	100 %	100 %	
Gostota [g/ml]	1,15 g/ml	1,13 g/ml	1,1 g/ml	1,13 g/ml	1,1 g/ml	1,1 g/ml	1,1 g/ml	1,1 g/ml	1,25 g/ml	
Količina nanosa [g/m <sup>2</sup> ]	~180 g/m <sup>2</sup>	~180 g/m <sup>2</sup>	~200 g/m <sup>2</sup>	~180 g/m <sup>2</sup>	~200 g/m <sup>2</sup>	~200 g/m <sup>2</sup>	~200 g/m <sup>2</sup>	~200 g/m <sup>2</sup>	~180 g/m <sup>2</sup>	
Vodoodpornost	vodoodporen	vodoodporen	vodoodporen	vodoodporen	vodoodporen	vodoodporen	vodoodporen	vodoodporen	vodoodporen	
Ekologija	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil	Brez formaldehida JAIA ***** F☆☆☆☆ Brez topil
Shranjevanje <sup>1</sup>	6 mesecev	3 mesece	3 mesece	3 mesece	3 mesece	3 mesece	3 mesece	3 mesece	6 mesecev	
Embalaza	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	800 g steklenice 20 kg kovinski sod 50/200 kg sod 1 tona kontejner	

<sup>1</sup> Normalni klimatski pogoji (20°C / 65% relativna ZV)